

TENCATE GEOSYNTHETICS Americas

## Mirafi<sup>®</sup> FW404



Mirafi<sup>®</sup> FW404 is composed of high-tenacity monofilament polypropylene yarns, which are woven into a stable network such that the yarns retain their relative position. Mirafi<sup>®</sup> FW404 geotextile is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). NTPEP Listed

| Mechanical Properties        | Test Method | Unit  | Minimum Average<br>Roll Value |             |
|------------------------------|-------------|---|-------------------------------|-------------|
|                              |             |   | MD                            | CD          |
| Grab Tensile Strength        | ASTM D4632  | lbs (N)   | 400 (1780)                    | 315 (1402)  |
| Grab Tensile Elongation      | ASTM D4632  | %   | 15                            | 15          |
| Trapezoid Tear Strength      | ASTM D4533  | lbs (N)   | 150 (668)                     | 165 (734)   |
| CBR Puncture Strength        | ASTM D6241  | lbs (N)   | 1150 (5118)                   |             |
|                              |             |   | Minimum I                     | Roll Value  |
| Percent Open Area            | COE-02215   | %   | 1.0                           |             |
| Permittivity                 | ASTM D4491  | sec <sup>-1</sup>                               | 0.9                           |             |
| Flow Rate                    | ASTM D4491  | gal/min/ft <sup>2</sup> (l/min/m <sup>2</sup> ) | 70 (2852)                     |             |
|                              |             |   | Maximum O                     | pening Size |
| Apparent Opening Size (AOS)  | ASTM D4751  | U.S. Sieve (mm)                                 | 40 (0.425)                    |             |
|                              |             |   | Minimum Test Value            |             |
| UV Resistance (at 500 hours) | ASTM D4355  | % strength retained                             | 90                            |             |

| Physical Properties              | Unit     | Roll Size              |  |
|----------------------------------|----------|------------------------|--|
| Roll Dimensions (width x length) | ft (m)   | 15 x 300 (4.57 x 91.4) |  |
| Roll Area                        | yd² (m²) | 500 (418)              |  |

Mirafi<sup>®</sup> is a registered trademark of Nicolon Corporation.

Copyright © 2015 Nicolon Corporation. All Rights Reserved.

365 South Holland Drive Pendergrass, GA 30567 Tel 706 693 2226 Tel 888 795 0808 Fax 706 693 4400 www.tencate.com



FGS000015 ETQR29

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.